

Gunze Kobunshi

July 01, 2009
Revised: January 21,2010

Technical Data Sheet

Kopalon Tube PTU403A

Film Highlights: 'PTU403A' is a heat-shrink tube for fluorescent lamps. It is ideal for fluorescent lamps with effective UV and fragment retention. It absorbs more than 99% of UV-A radiation and filters up to 400nm.

[Suggested Applications]

Food Plant, Medical Plant, Restaurant, Food and Clothing Store, Museum

1. Basic Properties

Properties	Item	Typical Values		Test Method
		MD	TD	
Density		1.35 g/cm ³		-
Mechanical	Tensile Strength	220MPa	180MPa	JIS K-7127
	Elongation	80 %	120 %	
	Young's modulus	1200MPa	800MPa	
	Tear Strength	340 N/mm	320 N/mm	JIS K-7129B
Electrical	Voltage Resistance	AC 14.0 kV/0.1mm		JIS C-2133
Enabled Temperature	Operating Range	-60 ~ 150 °C		JIS C-0025
	Continuous-Duty	125°C		
Shrinkage	80C	7%	9%	Gear Oven X 5M
	100C	25%	30%	
	120C	26%	34%	
	140C	26%	37%	
	160C	27%	39%	
	180C	27%	43%	

(Note) Above figures are measured values, not guaranteed.

2. Film Capability (Nominal Size)

- (1) Thickness: 0.1~0.12mm
- (2) Lay flat: 28~64mm.
- (3) Roll Lengths: 200~400 meters
- (4) Minimum Order Size: 10,000 meters

Gunze Kobunshi Corporation
PH: +81-6-6733-7060, Fax: +81-6-6733-7061
E-mail: yoji.togawa@gunze.co.jp